technical data sheet

SUPEX

2311

TECHNICAL INFORMATION

Structure

Sealable matt surface layer

Polypropylene core layer

Sealant layer

Description

SUPEX 2311 is a matt surface, coextruded biaxially oriented polypropylene film. Matt side is treated. Both sides are heat sealable.

Properties

- Broad seal range
- Excellent hot tack and heat seal strenght
- A to B sealing capability
- Good moisture barrier
- Excellent resistance to chemicals, greases and oils
- Excellent ink and coating ADHESRON
- Low static property

Applications

A general purpose packaging film where the mattness effect is value added property. Can be used as single ply and as lamination base film for different applications.

It is recommended for coffee, light foods, confectionary and soap overwrap packaging applications.



		BOPP TECHI	NICAL PROPE	RTIES	
SUPEX 2311					TEST METHOD
THICKNESS		MICRON	20	50	
		GAUGE	78,7	196,9	ASTM D 2673
YIELD		m ² /kg	57,5	23	ASTM D 2673
		in ² /Lbs	40426	16170	
TENSILE STRENGTH	MD	N/mm ²	140		ASTM D 882
		Ib/in ²			
		N/mm ²	230		
	TD	Ib/in ²	33331		
ELONGATION AT BREAK	MD	%	150		The state of the s
	TD	%	60		ASTM D 1204
THERMAL SHRINKAGE	MD	%	4		ASTM D 1204
	TD	%	2		
COEFFICIENT		Film/Film	0,30		ASTM D 1894
OF FRICTION		Film/Metal	0,20		
HAZE		%	70	70	ASTM D 1003
GLOOS(45°)	ALL SEL	%	10	10	ASTM D 2457
SURFACE TENSION	Dyn/cm 38		38	ASTM D 2578	
HEATSEAL RANGE	V-F	°F	248-293		ASTM F 88
		°C	120-145		
HEATSEAL RANGE		N/15mm	>2,5		ASTM F 88,

The information contained in this data sheet is true and accurate according to current state of our knowledge and intented to give general information on our products and their applications. Above values are to be considered as guidelines and not as product specifications. Since the actual conditions of use are beyond our control, users are advised to make their own tests at their specifyc conditions of laboratory and/or actual use.

We suggest our customers to determine final suitability for their specific end uses

Also be advised that information on this data sheet shall not be construed as an inducement or recommendation to use any process or to manufacture or use any product in conflict with existing, pending or future patents.

For related spec sheet with tolerance values, please contact our sales departmens

Factory&HeadOffice: 3. Organize Sanayi Bölgesi, Baspinar, Gaziantep-Türkiye Phone: +90-342-337 33 00 (20 Lines)- Fax:+ 90-342-337 28 70 e-mail: export@superfilm.com

Istanbul Liasion Office: Phone:+ 90 –212-474 54 74 (10 Lines) · Fax:+ 90-212-474 54 84 Izmir Liasion Office: Phone:+ 90-232-441 75 69 (3Lines) · Fax:+ 90-232-441 70 46

U.S.A Head Office Phone:+ 1 –614-799 99 94 Fax :+ 1-614-799 99 95

e-mail: usahead@superfilm.com