

	Ref. STD	Unit of meas.	TECHNICAL SPECIFICATIONS			
Substance	ISO 536	g/m <sup>2</sup>	115			
Caliper	ISO 534	µm	130			
Roughness Bendtsen	ISO 8791-2	ml/min	140			
Roughness Bendtsen back side	ISO 8791-2	ml/min	700			
Gloss Gardner	ISO 8254-1	%	28			
Photovolt Brightness	ISO 2470	%	89			
Photovolt Opacity	ISO 2471	%	98			
MD Tensile Strength	ISO 1924-1/2	KN/m	5,5			
CD Tensile Strength	ISO 1924-1/2	KN/m	3,5			
Tearing strength MD	ISO 1974	mN	850			
Tearing strength CD	ISO 1974	mN	950			
Wet Breaking Load MD	ISO 3781	KN/m	1			
Wet Breaking Load CD	ISO 3781	KN/m	0,8			
% wet tensile strenght	ISO 3781	%	22			
Cobb 60 back side	ISO 535	g/m <sup>2</sup>	25			

**Notes:**

Finishing **Matt**  
 Printing method **Heatset Web-offset - Digital**  
 Applications

Values referred to each quality are to be considered as reference data and could change without notice. Each value is subject to trade tolerances.